

PHENOLIC COTTON CLOTH LAMINATED SHEETS

Tested Item	单位 (unit)	标准 standard	实测结果 tested result
1.Bending elastic modulus of appearance	Mpa	2100min	
2.Peel strength parallel to laminations	Mpa	7.5 min	
3.Tensile strength	Mpa	24 min	
4.Breakdown voltage parallel to laminations((in 90±2℃ oil)	Kv	0.3 min	
5.Density	g/cm ³	1.3-1.4	
	mm	980*1980 2070*1020	或
6.reference standard	Enterprise's standard		